

TECHNICAL INFORMATION PRELIMINARY



-Wine Label-

WS Ivory/WL01/WG62

PHYSICAL CHARACTERISTICS

Facestock

Woodfree paper with high opacity and wet strength features. It is suitable for offset, flexo, silk screen and stamping printing process.

Basis Weight ISO 536 : 90 gsm
Caliper ISO 534 : 126 μm

Adhesive

A general purpose emulsion acrylic permanent with excellent water resistance and develop very good adhesion on paper facestock. Features excellent initial tack and adhesion even when applied to low surface energy substrates.

Minimum Application Temperature : +5°C
Product Functional Service Temperature: -20°C / +80°C

Liner

A super-calendered white glassine paper.

Basis weight ISO 536 : 60 gsm
Caliper ISO 534 : 54 μm

PERFORMANCE CHARACTERISTICS

Properties	Test Method	Typical values
Initial Tack on Glass	FINAT FTM9	13.0-16.0 N/25mm
Adhesion to Stainless Steel	FINAT FTM2	7.0 N/25mm (20mins)
Total Product Caliper	ISO 534	197 μm

Shelf life

1 year when stored at 22°C and 50% RH