

Product: Conqueror Laid

Category: Folio Papers - Specialty Paper

Country of Origin: United Kingdom

Technical specifications:

Basis Weight	g/m ²	90	100	120	220	300	400
Thickness	µms ISO 534	126	141	165	322	442	588
Roughness	ml/min ISO2494	850	850	900	1700	1700	1700
Opacity	% ISO 2471	90	92	94	-	-	-
pH Value/Archival	TAPPI 5290M	≈7.5	≈7.5	≈7.5	≈7.5	≈7.5	≈7.5
Relative Humidity	% TAPPI T502	35-55	35-55	35-55	40-60	40-60	40-60
Stiffness MD	mN ISO2493	-	-	-	100	240	610
Stiffness CD	mN ISO2493	-	-	-	60	130	300

These characteristics are average values supplied for guidance purposes

Certificates

- FSC Certified: Mix, ISO 14001 Environmental Management System, Made Carbon Neutral.
- ISO 9706 Longlife, ISO 9001 Quality Management System

Print & Finish Suitability

<input checked="" type="radio"/> Creasing	<input checked="" type="radio"/> Foiling	<input checked="" type="radio"/> Laser
<input checked="" type="radio"/> Die-Cutting	<input checked="" type="radio"/> Folding	<input checked="" type="radio"/> Scoring
<input type="radio"/> Digital	<input checked="" type="radio"/> Inkjet	<input checked="" type="radio"/> Varnishing: UV not recommended
<input checked="" type="radio"/> Embossing	<input type="radio"/> Film Laminating	<input type="radio"/> Screen Ruling:
<input type="radio"/> Other:		

Applications

<input type="radio"/> Annual Reports	<input checked="" type="radio"/> Direct Mail	<input type="radio"/> Outdoor Use
<input checked="" type="radio"/> Brochures	<input type="radio"/> Folders	<input type="radio"/> Packaging
<input checked="" type="radio"/> Corporate Identity	<input checked="" type="radio"/> Invitations	<input checked="" type="radio"/> Presentation Material
<input checked="" type="radio"/> Other: Cards, stationery, menus		