

Product: Grange Tints

Category: Folio Papers - Uncoated

Country of origin: Indonesia

Technical specifications:

Basis Weight	g/m ²	80
Thickness	µms ISO 534	104±8
Smoothness Bekk	sec/10cc	15-45
Roughness	ml/min	80-280
pH Value/Archival		7-8
Relative Humidity		50-55
Porosity	%	5-25
Stiffness MD	mNm	≥0.40
Stiffness CD	mNm	≥0.20
Surface Strength	Wax No.	≥14
Cobb. 1 min (multisheet)	g/m ²	≤25

These characteristics are average values supplied for guidance purposes

Certificates

- 100% PEFC Certified, ISO 14001 Environmental Management System

Print & Finish Suitability

<input checked="" type="radio"/> Creasing	<input type="radio"/> Foiling	<input checked="" type="radio"/> Laser
<input type="radio"/> Die-Cutting	<input checked="" type="radio"/> Folding	<input checked="" type="radio"/> Scoring
<input type="radio"/> Digital	<input checked="" type="radio"/> Inkjet	<input type="radio"/> Varnishing
<input type="radio"/> Embossing	<input type="radio"/> Film Laminating	<input type="radio"/> Screen Ruling: 150 - 200 lpi
<input checked="" type="radio"/> Other: Dry Toner		

Applications

<input checked="" type="radio"/> Annual Reports	<input checked="" type="radio"/> Direct Mail	<input type="radio"/> Outdoor Use
<input checked="" type="radio"/> Brochures	<input type="radio"/> Folders	<input type="radio"/> Packaging
<input type="radio"/> Corporate Identity	<input type="radio"/> Invitations	<input type="radio"/> Presentation Material
<input checked="" type="radio"/> Other: Stationery		