

Product: Raflamatt Matt Coated

Category: Folio Papers - Self Adhesive

Country of origin: Poland

Technical specifications:

SELF-ADHESIVE	SHEETS
FACE	RAFLAMATT/SHEETS
Matt Coated	SH (sales code)
Product	White, matt, machine coated, woodfree label paper.
Use	For high quality labels with multi-colour printing.

Typical technical values

Substance	80	g/m ²	ISO 536	
Caliper	70	µm	ISO 534	
Tensile strength MD	5.0	kN/m	ISO 1924/1	
Tensile strength CD	2.0	kN/m	ISO 1924/1	
Brightness	97	%	ISO 2470/1	
Roughness	2.4	µm	ISO 8791	PPS 10
Opacity	93	%	ISO 2471	
Gloss	20	%	Hunter 75°	

Printability Offset, flexography, letterpress.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

Product: Raflatac Matt Coated

Category: Folio Papers - Self Adhesive

Country of origin: Poland

Technical specifications:

ADHESIVE	SP34 GREENTAC PLUS		
Permanent	SP34 (sales code)		
Type	General permanent adhesive for sheets.		
Composition	Modified acrylic dispersion.		
Use	A very good adhesive for general use with paper labels. Good heat resistance. Improved guillotine properties. Recycling properties are optimized based on up-to-date knowledge (Ingede project 5397 PTS).		

Typical technical values

Tack min	10	N	FTM 9
Shear min	2	h	FTM 8
Labelling temperature min	5	°C	
Service temperature min	-10	°C	
Service temperature max	100	°C	

Limitations Should not be used in cold environments. Not recommended for labelling highly curved surfaces.

Approvals Please see DoC

Shelf life 4 years at +20°C and RH 50% from the date of manufacture.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

Product: Raflatac Matt Coated

Category: Folio Papers - Self Adhesive

Country of origin: Poland

Technical specifications:

SELF-ADHESIVE	SHEETS
BACKING	KRAFT SPECIAL 90 FSC
Kraft	EJB (sales code)
Product	White woodfree kraft backing paper
Use	Backing paper for reels and sheets in information labelling. Not to be used in photocell dispensing systems.

Typical technical values

Substance	86	g/m ²	ISO 536
Caliper	87	µm	ISO 534
Tensile strength MD	8.7	kN/m	ISO 1924
Tensile strength CD	3.8	kN/m	ISO 1924

Sustainability The product named as FSC is registered to SGSCH-COC-004879 FSC TM Mix Credit.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.