

Technical specification sheet

Ball & Doggett

ballanddoggett.com.au

Product: Yupo Fast Dry

Category: Folio Papers - Synthetic

Country of Origin: Japan

Technical specifications:

| 88.7gsm / 110µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 110 |
| Basis weight | | g/m ² | 88.7 |
| Density | | g/c m ³ | 0.81 |
| Whiteness | | % | 97 |
| Opacity | | % | 96.5 |
| Gloss | Top | % | 51 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 50 |
| | TD | | |
| Surface resistance | | Ω | 1x10 ¹¹ |

| 100.1gsm / 130µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 130 |
| Basis weight | | g/m ² | 100.1 |
| Density | | g/c m ³ | 0.77 |
| Whiteness | | % | 97 |
| Opacity | | % | 97 |
| Gloss | Top | % | 51 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 60 |
| | TD | | |
| Surface resistance | | Ω | 1x10 ¹¹ |

| 115.5gsm / 150µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 150 |
| Basis weight | | g/m ² | 115.5 |
| Density | | g/c m ³ | 0.77 |
| Whiteness | | % | 97 |
| Opacity | | % | 98 |
| Gloss | Top | % | 51 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 80 |
| | TD | | |
| Surface resistance | | Ω | 1x10 ¹¹ |

Technical Specification sheet

Ball & Doggett

ballanddoggett.com.au

Product: Yupo Fast Dry

Category: Folio Papers - Synthetic

Country of Origin: Japan

Technical specifications: (continued)

| 158gsm / 200µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 200 |
| Basis weight | | g/m ² | 158.0 |
| Density | | g/c m ³ | 0.79 |
| Whiteness | | % | 97 |
| Opacity | | % | 98.5 |
| Gloss | Top | % | 50 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 125 |
| | TD | | 275 |
| Surface resistance | | Ω | 1x10 ¹¹ |

| 200gsm / 250µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 250 |
| Basis weight | | g/m ² | 200 |
| Density | | g/c m ³ | 0.80 |
| Whiteness | | % | 97 |
| Opacity | | % | 99 |
| Gloss | Top | % | 49 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 200 |
| | TD | | 420 |
| Surface resistance | | Ω | 1x10 ¹¹ |

| 234gsm / 300µms | | | |
|------------------------------|--------|--------------------|--------------------|
| Caliper | | µm | 300 |
| Basis weight | | g/m ² | 234 |
| Density | | g/c m ³ | 0.78 |
| Whiteness | | % | 97 |
| Opacity | | % | 99.5 |
| Gloss | Top | % | 46 |
| | Bottom | | |
| Stiffness (clark S Value) | MD | S Value | 270 |
| | TD | | 600 |
| Surface resistance | | Ω | 1x10 ¹¹ |