

Koala Kraft

Tough Australian made kraft board. This uncoated two sided board is perfect for a variety of packaging applications from rustic designer envelopes to heavy duty drink carrier packs.

- / Made from 80% virgin fibre and 20% recycled fibre
- / Suitable for direct food contact
- ✓ Perfect for custom packing and premium brand owners
- Typical packaging applications include: Kraft wrapping, disposable tablecloths, dry, chilled and frozen foods, drink carrier packs, heavy duty envelopes, suspended packaging for tools, batteries and heavy spare parts
- Available in –
 250ums/200gsm
 300ums/225gsm
 370ums/300gsm
 420ums/337gsm
 460ums/370gsm
 500ums/400gsm
 560ums/440gsm

KOALA KRAFT







Range Unit Property Property Range Unit Aim 200 225 300 337 370 400 440 Aim g/m² Min 194 218 291 327 359 385 Min 423 Substance g/m² Substance Max 206 232 309 347 381 415 Мах 457 7.5 7.5 8.2 Aim 7.5 7.5 7.5 7.5 Aim Moisture Moisture Min % Min % 6 6 6 6 6 6 67 Max Мах 9.7 kPa 880 990 1200 1348 1406 1520 kPa 1600 Min 800 900 1050 1179 1220 1320 Min 1452 Aim kPam²/g 4.4 4.4 4.0 4.0 3.8 3.8 Aim kPam²/g 3.6 Burst index Burst index Min 4.0 4.0 3.5 3.5 3.3 3.3 Min 3.3 kN/m 4.34 6.00 7.80 8.30 Aim 3.86 6.87 7.40 Aim kN/m SCT cd SCT cd Min 3.32 3.74 4.98 5.40 5.92 6.40 Min 7.04 Aim 19.3 19.3 20.0 20.0 19.5 19.0 SCT index SCT index Min 16.6 16.6 16.6 16.0 16.0 16.0 Min 16.0 Aim 120 120 120 120 120 Aim 40 Cobb Cobb 30 min (T Liner) Min g/m^2 90 90 90 90 90 90 Min 20 2 min (T Liner) 150 150 150 Max 150 150 150 Max 50 Aim 55 55 55 Aim 40 Cobb 1 min (B Liner) Min g/m^2 35 35 35 35 35 35 Min 20 2 min (T Liner) 90 90 90 50 Max 90 90 90 Max 1700 2000 2100 2300 2500 2700 Roughness Roughness ml/min ml/min (Bendtsen) (Bendtsen) Max 2100 2400 2800 Max 3300 120 120 120 120 120 120 Aim 125 Aim Scott Scottbond Scottbond units

