

**Product:** Avery Dennison 8826 Wall Textile Hi-Tack



**Category:** Display & Visual - Solvent, Eco Solvent, Latex

## Technical specifications:

Avery Dennison Multi Purpose Inkjet 8826 Wall Textile Hi-Tack is a flexible textile film with a matte white canvas finish specifically designed for wall coverings and wall art graphics applications.

The material is suitable for digital printing technologies: solvent, eco-solvent, latex and UV. A high-tack adhesive makes the film a good match for many different surfaces, including challenging low surface energy substrates. MPI 8826 Wall Textile Hi-Tack is an excellent choice for hospitals, sporting arenas, hotels and any contract wall covering.

### Features:

- PVC free
- New exclusive design opportunities using digitally printable textile film
- Hi-Tack adhesive suitable for difficult to adhere surfaces
- Additional facestock body that enhances ease of application
- High opacity to fully cover eventual imperfections of the substrate
- Premium material with excellent printability across a wide range of technologies and inks
- Suitable for smooth walls - no primer needed
- Hi tack adhesive designed for low energy and difficult to adhere substrates.

### Conversion\*:

Avery Dennison Multi Purpose Inkjet MPI 8826 Wall Textile is a multi-purpose textile product, developed for use on various wide format printers using Latex, Solvent, Eco/mild solvent and UV curable inks. As the material has a high calliper, it is important to validate before printing, whether the printer can handle the rolls. To achieve the best possible print quality, please make sure the correct ICC Profile and printer settings are used. For additional information related to wall application, please refer to Avery Dennison Instructional bulletin 1.6.

In order to avoid sub-optimal performance of the product in application, it is essential to make the correct product choice for the application. Before starting a project it is always recommended to do a pilot application to ensure satisfactory product performance before a full roll out of the project. In case of uncertainty you may always reach out to your Avery Dennison contact for further help or recommendations.

- |                                            |                                                     |
|--------------------------------------------|-----------------------------------------------------|
| <input type="radio"/> Flat bed cutters     | <input type="radio"/> Cold overlaminating           |
| <input type="radio"/> Friction fed cutters | <input type="radio"/> Electrostatic printing        |
| <input type="radio"/> Die cutting          | <input checked="" type="radio"/> Latex inkjet       |
| <input type="radio"/> Thermal transfer     | <input checked="" type="radio"/> Eco solvent inkjet |
| <input type="radio"/> Screen printing      | <input checked="" type="radio"/> Solvent inkjet     |
| <input type="radio"/> Offset printing      | <input checked="" type="radio"/> UV curable inkjet  |

\* Always test with your combination of printer and inks prior to commercial use.

### Description:



**Face:** 254µm textured white PET textile with matte white canvas finish



**Adhesive:** Permanent, hi-tack, grey acrylic



**Backing:** One side polyethylene coated kraft paper 143 g/m<sup>2</sup>



**Indoor life:** Up to 4 years

### Application surface:

Flat smooth surface  
Low surface energy substrates

### Common Applications:

- Interior decoration
- Indoor advertising
- Retail wall graphics
- Wall decorations
- Exhibition wall graphics

## General

<b>Calliper, face film</b>	ISO 534	254 micron
<b>Calliper, face film &amp; adhesive</b>	ISO 534	294 micron
<b>Dimensional stability</b>	FINAT FTM 14	0 mm
<i>Note: Ink loads in excess of 250% may cause increased shrinkage of the printed film</i>		
<b>Adhesion, initial</b>	FINAT FTM-1, Stainless steel	470 N/m
<b>Adhesion, ultimate</b>	FINAT FTM-1, Stainless steel	560 N/m
<b>Adhesion, initial</b>	FINAT FTM-1, HDPE	400 N/m
<b>Adhesion, ultimate</b>	FINAT FTM-1, HDPE	420 N/m
<b>Opacity</b>	X-rite SP64	>99%
<b>Flammability</b>	Self extinguishing	
<b>Shelf life</b>	Stored at 23° C/50-55 % RH	1 year
<b>Expected Durability</b>	Vertical exposure indoor ^	4 years
^ See ICS Performance Guarantee Durability Bulletin for your specific printer and ink combination for further information		

## Thermal

<b>Application temperature</b>	≤10°C
<b>Temperature range</b>	- 40°C to + 80°C

## Note

Materials have to be properly dried before further processing, for example laminating, varnishing or application. The residual solvents could change the products' specific features.

For good print and converting result we recommend to let the rolls acclimatize in the print/lamination room at least 24h. before printing or converting. Too much temperature or humidity deviation between material and room climate can cause layflatness and/or printability issues.

Generally, constant material storage conditions of ideally 20°C (+/-2°C) /50% RH (+/- 5%), without too big climate deviations, will support a more robust and stable printing/converting process. For further details, please refer to TB 1.11.

## Testing Methods

### Dimensional stability:

Is measured on a 150 x 150 mm aluminium panel to which a specimen has been applied; 72 hours after application the panel is exposed for 48 hours to + 70°C, after which the shrinkage is measured.

### Adhesion:

(FTM-1, FINAT) is measured by peeling a specimen at a 180° angle from a stainless steel or float glass panel, 24 hours after the specimen has been applied under standardised conditions. Initial adhesion is measured 20 minutes after application of the specimen.

### Flammability:

A specimen applied to aluminium is subjected to the flame of a gas burner for 15 seconds. The film should stop burning within 15 seconds after removal from the flame.

### Temperature range:

A specimen applied to stainless steel is exposed at high and low temperatures and brought back to room temperature. 1 hour after exposure the specimen is examined for any deterioration. Note: Prolonged exposure to high and low temperatures in the presence of chemicals such as solvents, acids, dyes, etc. may eventually cause deterioration.

### Chemical Resistance:

All chemical tests are conducted with test panels to which a specimen has been applied. 72 hours after application the panels are immersed in the test fluid for the given test period. 1 hour after removing the panel from the fluid, the specimen is examined for any deterioration.

### Corrosion Resistance:

A specimen applied to aluminium is exposed to saline mist (5% salt) at 35°C. After exposure, the film is removed and the panel is examined for traces of corrosion.

### Important

Information on physical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of any material for their specific use.

All technical data is subject to change without prior notice.

### Warranty

Avery Dennison® materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give guarantee, warranty, or make any representation contrary to the foregoing.

All Avery Dennison® materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

### Expected Durability

The expected durability of Avery Dennison films are defined as the expected performance life of the Avery Dennison graphic film(s) within Zone 1 of the Avery Dennison zone system, in outdoor vertical exposure conditions.

The actual performance life will depend on a variety of factors, including selection and preparation of substrate, angle and direction of exposure, application methods, environmental conditions and cleaning/maintenance of the films.

In case of films used in areas of high temperatures or humidity, high altitudes and industrially polluted areas the performance will be further reduced.

### Expected Durability and Warranted Period Definitions

Expected durability is the expected period of time defined in the product data sheet, the product should, but is not warranted to, perform satisfactorily when applied in vertical exposure conditions as defined in Instructional Bulletin 1.30. The warranted period as defined in the appropriate ICS Performance Guarantee Bulletin, is the maximum period of time Avery Dennison will warrant the finished products performance in accordance with ICS Performance Guarantee Terms and Conditions 1.0, provided that the film is properly stored, converted and installed in accordance with Avery Dennison guidelines.

+Compatible with most printer and ink combinations. Test prior to use.

Certified for  
HP Latex Inks

For further details please check the HP media locator website at: [hp.com/go/mediasolutionslocator](http://hp.com/go/mediasolutionslocator)