

Product: Supa Claycote

Category: Sign, Display & Digital - Rigid

Country of Origin: Australia

Technical specifications:

Manufactured Made in Australia from local and imported products
Style Smooth print facing board with flute corrugation centre

TECHNICAL INFORMATION

PROPERTY, UNIT	METHOD	STANDARD	VALUE (4mm)	Value (5mm)
Thickness (mm)		ISO 536	4mm	5mm
Twin - Facing structure			195gsm	220gsm
Centre structure			E Flute	E B Flute
Bending stiffness CD mNm	Taber 15°	ISO 2493	4.0	5.7
Bending stiffness MD mNm	Taber 15°	ISO 2493	8.0	11.3
Thickness µm		ISO 534	310	360
Moisture content %		ISO 287	7.0	7.0
Smoothness top	PPS10	ISO 8791-4	<1.4	<1.4
Brightness top %	Illumination C/2°	ISO 2470-1	85	85
Water absorption top, back g/m ²	Cobb 3min	ISO 535	≤50	≤50
Water absorption middle g/m ²	Cobb 3min	ISO 535	≤40	≤40

Conversion⁺

- | | |
|---|---|
| <input type="checkbox"/> Flat bed cutters | <input type="checkbox"/> Cold overlaminating |
| <input type="checkbox"/> Friction fed cutters | <input type="checkbox"/> Aqueous |
| <input type="checkbox"/> Die cutting | <input checked="" type="checkbox"/> Latex inkjet |
| <input type="checkbox"/> Thermal transfer | <input type="checkbox"/> Eco Solvnt inkjet |
| <input checked="" type="checkbox"/> Screen printing | <input type="checkbox"/> Solvent inkjet |
| <input type="checkbox"/> Offset printing | <input checked="" type="checkbox"/> UV curable Inkjet |

⁺Always test with your combination of printer and inks prior to commercial use.